

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)


EP 1 202 324 A1

(12)

EUROPEAN PATENT APPLICATION(43) Date of publication:
02.05.2002 Bulletin 2002/18(51) Int Cl.⁷: **H01J 61/30, H01J 61/36**(21) Application number: **01309263.0**(22) Date of filing: **31.10.2001**(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**
Designated Extension States:
AL LT LV MK RO SI(72) Inventor: **Miyazawa, Sugio,**
c/o NGK Insulators, Ltd.
Nagoya-shi, Aichi-ken, 467-8530 (JP)(30) Priority: **31.10.2000 JP 2000333372**(74) Representative: **Paget, Hugh Charles Edward et al**
MEWBURN ELLIS
York House
23 Kingsway
London WC2B 6HP (GB)(71) Applicant: **NGK INSULATORS, LTD.**
Nagoya-City, Aichi Prefecture 467-8530 (JP)**(54) Ceramic envelope for high intensity discharge lamp**

(57) A ceramic envelope for high intensity discharge lamp comprises a cylindrical barrel section 1 that forms an electric discharge light emitting space, an annular closing section 2, that closes both ends of the barrel section 1. Capillary sections 3 receive electric discharge electrodes to be outwardly protruded so as to be opposed to each other from the substantial center position of both closing sections. The envelope is made of an

alumina-based material and is formed so as to have light transmitting properties. At an interior face of a barrel section 2 and an electric discharge light emitting space corner of the barrel section 1, a rounded interior corner 1.0 mm in curvature diameter is provided so that the thickness is gradually changed. In this manner, a ceramic envelope capable of extended service life is provided even if the electric discharge light emitting space is cylindrical.

FIG. 1**EP 1 202 324 A1**

Description

BACKGROUND OF THE INVENTION

FIELD OF THE INVENTION

[0001] The present invention relates to a ceramic envelope made of a light transmission ceramics used for a high intensity discharge lamp such as high pressure sodium lamp or a metal halide lamp.

DESCRIPTION OF RELATED ART

[0002] Conventionally, an electric discharge lamp using a ceramic envelope made of light transmission ceramics is widely used as a ceramics metal halide lamp. In this type of the lamp, an electric discharge light emitting space is formed in a cylindrical shape. Such a ceramic envelope has a structure as shown in FIG. 3A and FIG. 3B, i.e., a cylindrical barrel section 10 forming an electric discharge light emitting space at its center. Its left and right ends are closed by an annular closing material 11, and its structure is provided such that a capillary tube 12 is connected in facing opposite to each other at the substantial center of the closing material 11. Then, after a light emitting substance or startup gas is sealed in an electric discharge light emitting space, an electrode is inserted into the capillary tube 12, and is sealed, thereby forming an electric discharge lamp.

[0003] These sections such as the barrel section 10, closing plate 11, and capillary tube 12 are each molded independently, and are integrally coupled with each other, thereby forming a ceramic envelope.

[0004] In the above ceramic envelope having the cylindrical electric discharge light emitting space, a temperature at a corner part of a cylinder is the lowest during lighting. Thus, a light emitting substance, which is a corrosive substance, easily accumulates at that site. As a result, although a light color change in the lighting direction is reduced, corrosion at the corner is easily advanced because the light emitting substance easily accumulates. The corrosion at that portion determines a service life of the lamp.

[0005] In addition, in such a ceramic envelope having a cylindrical electric discharge space, there is employed a fabrication method in which plural parts are assembled and bonded due to contraction action during burning. As shown in FIG. 3A, which is a partially enlarged view of the envelope, a wedge shaped cavity 13 is easily formed at a bonding section. In particular, a light emitting substance easily enters the cavity 13 generated at the corner of the barrel section 10, which causes corrosion, and impairs extended service life. Further, such a wedge shaped cavity easily causes stress concentration, and extended service life is impaired due to a thermal stress generated during lighting.

SUMMARY OF THE INVENTION

[0006] The present invention has been made in order to solve the foregoing problem. It is an object of the present invention to provide a ceramic envelope for high intensity light emitting lamp capable of extending the service life of the lamp even if an electric discharge light emitting space is formed in a cylindrical shape.

[0007] According to a first aspect of the present invention, there is provided a ceramic envelope made of a light transmission ceramics for high intensity discharge lamp comprising a cylindrical barrel section that forms an electric discharge light emitting space, an annular closing section that closes both ends of the barrel section, and a capillary section that inserts and fixes an electric discharge electrode to be outwardly protruded so as to be opposed to each other from the substantial center of both closing sections.

R is provided at an end of an interior face of the barrel section that is a boundary part between said barrel section and closing section, thereby avoiding a factor for impairing extended service life due to generation of the wedge shaped cavity section.

Preferably the R value is from 0.01 mm to 2.0 mm.

[0008] Additional objects and advantages of the invention will be set forth in the description which follows, and in part will be obvious from the description, or may be learned by practice of the invention. The objects and advantages of the invention may be realized and obtained by means of the instrumentalities and combinations particularly pointed out hereinafter.

BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWINGS

[0009] The accompanying drawings illustrate preferred embodiments of the present invention, and together with the general description given above and the detailed description of the preferred embodiments given below, serve to explain the principle of the present invention.

[0010] FIG. 1 is an illustrative cross section of a ceramic envelope for high intensity discharge lamp illustrating one embodiment of the present invention.

[0011] FIG. 2 is an illustrative cross section of a ceramic envelope for high intensity discharge lamp illustrating another embodiment of the present invention.

[0012] FIG. 3A and FIG. 3B are illustrative cross sections of a conventional ceramic envelope for high intensity discharge lamp, in which reference numeral 1 denotes a barrel section, reference numeral 2 denotes a capillary section, and reference numeral 3 denotes a boundary part.

DETAILED DESCRIPTION OF THE INVENTION

[0013] Hereinafter, preferred embodiments of the present invention will be described in detail with refer-

ence to the accompanying drawings.

[0014] In FIG. 1, an example of a ceramic envelope for high intensity discharge according to the present invention is shown. This envelope has a cylindrical barrel section 1 that forms an electric discharge light emitting space at its center. Its both ends are closed by an annular closing sections 2, 2, and capillary sections 3, 3 having their small diameters are brought into protrusive contact with each other so as to be in parallel to the barrel section 1 from the center of the closing section 2 and so as to be opposed to each other. This capillary section 3 is intended to insert, seal, and fix a rod shaped electrode conductor (not shown) having an electric discharge electrode provided at its tip end.

[0015] These members, each of which is made of an alumina-based material, are molded, assembled, and fired, whereby they are formed so as to have light transmission properties. An example of dimensions of each section is shown here. An outer diameter D1 of the barrel section 1 is 11.6 mm, an inner diameter D2 is 9.4 mm, a length L1 is 19 mm, thickness W1 of the closing section is 3 mm, and a full length L2 of a light emitting tube is 47 mm.

[0016] In addition, as shown in one of the enlarged view, at an interior face of the barrel section 1 at the boundary part 4 with the closing section 2 that is a corner of an electric discharge light emitting space, at the interior face a rounded concave corner is provided to join smoothly the inner face of the barrel portion and the inner face of the closing section. This concave corner, as seen in axial section of the envelope, has a diameter of curvature R of 1.0 mm. This rounded corner prevents generation of a wedge at the electric discharge light emitting space corner.

[0017] By providing R at the corner of the electric discharge light emitting space of the easily corroded barrel section, the generation of a wedge shaped cavity at the corner can be prevented, and the service life can be extended.

[0018] In this case, the R value causes small effect if the value is smaller than 0.01 mm. In addition, if it exceeds 2.0 mm, the lamp efficiency is lowered due to an increase of ceramics capacitance, and further, light emission substance hardly accumulates at the corner. Consequently, advantageous effect of the cylindrical shaped electric discharge light emitting space is lowered. Thus, the value ranging from 0.01 mm to 2.0 mm is preferable. In particular, the value ranging from 0.3 mm to 1.0 mm is more preferable.

[0019] FIG. 2 shows another embodiment of the present invention. The figure also shows a case in which the entirety of the barrel section 1, closing section 2, and capillary section 3 are integrally molded. Materials and outward forms are the same as described in the above embodiments.

[0020] In integral molding in such a shape, the barrel section, closing section, and capillary section can be easily molded without any interface as compared with

the above embodiments. This is because the entire water content ratio or partial water content ratio as well as the composition of each section must be finely adjusted so as to generate no interface in the above embodiments.

[0021] By means of a lost wax or by applying a frost molding technique, injection molding technique, or gel casting technique to the lost wax, such integration molding can be easily carried out. By carrying out integral molding, a wedge shaped cavity is not formed, and the service life can be extended constantly. In addition, by carrying integral molding, R can be easily provided at a boundary part between the barrel section 1 and the closing section 2. By providing R, stress concentration hardly occurs and then a crack hardly occurs, which contributes to further extended service life.

[0022] R may be provided at only one site of the left and right corners of the electric discharge light emitting space. In the case where the ceramic envelope is used in an erect condition, a light emitting substance easily accumulates at one side of the bottom part. Thus, R may be provided at downward side.

[0023] Additional advantages and modifications will readily occur to those skilled in the art. Therefore, the invention in its broader aspect is not limited to the specific details and representative embodiments shown and described herein. Accordingly, various modifications may be made without departing from the spirit or scope of the general inventive concept.

Claims

1. A ceramic envelope made of a light transmission ceramics for high intensity discharge lamp comprising:

a barrel section that forms an electric discharge light emitting space;
annular closing sections that close both ends of the barrel section, respectively; and
capillary section to receive electric discharge electrodes to be protruded so as to be opposed to each other from the substantial center of both closing sections,

wherein at at least one of the boundary parts between said barrel section and said closing sections, a rounded interior corner is provided at the end of the barrel section.

2. A ceramic envelope for high intensity discharge as claimed in claim 1, wherein the diameter of curvature of the corner (R) is from 0.01 mm to 2.0 mm.

FIG.1




FIG.2





FIG.3





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 30 9263

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	GB 1 360 340 A (DEGUSSA) 17 July 1974 (1974-07-17) * claims 1,2; figure 1 *	1	H01J61/30 H01J61/36
X	EP 0 722 183 A (NGK INSULATORS LTD) 17 July 1996 (1996-07-17) * column 5, line 1 - line 52 * * column 9, line 55 - column 13, line 58; figures 1-8 *	1	
A	EP 0 284 576 A (LUMALAMPAN AB) 28 September 1988 (1988-09-28) * abstract; figures 4-6 *	1	
A	EP 0 220 633 A (GEN ELECTRIC) 6 May 1987 (1987-05-06) * claims 1,2; figures 1-3 *	1	
A	PATENT ABSTRACTS OF JAPAN vol. 009, no. 136 (E-320), 12 June 1985 (1985-06-12) & JP 60 020446 A (MITSUBISHI DENKI KK), 1 February 1985 (1985-02-01) * abstract *	1	TECHNICAL FIELDS SEARCHED (Int.Cl.7) H01J
A	PATENT ABSTRACTS OF JAPAN vol. 1998, no. 14, 31 December 1998 (1998-12-31) & JP 10 247476 A (TOSHIBA LIGHTING & TECHNOL CORP), 14 September 1998 (1998-09-14) * abstract *	1	
A	US 5 635 794 A (KOERFER GUENTER) 3 June 1997 (1997-06-03) * abstract; figure 2 *	1	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 31 January 2002	Examiner Deroubaix, P
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 03/82 (P04001)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 30 9263

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

31-01-2002

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
GB 1360340	A	17-07-1974	DE 2144486 A1	15-03-1973
			AT 287492 B	25-01-1971
			CH 446900 A	15-11-1967
			CH 443914 A	15-09-1967
			CH 466715 A	15-12-1968
			CH 444892 A	15-10-1967
			CH 463281 A	30-09-1968
			CH 463282 A	30-09-1968
			CH 451707 A	15-05-1968
			DE 1302770 B	28-11-1974
			DE 1447876 A1	17-04-1969
			DE 1497100 A1	30-04-1969
			DE 1611377 A1	23-12-1970
			DE 1797515 A1	15-04-1971
			FR 1434114 A	08-04-1966
			FR 2152556 A1	27-04-1973
			GB 1074866 A	05-07-1967
			GB 1071028 A	07-06-1967
			GB 1071029 A	07-06-1967
			GB 1071030 A	07-06-1967
			GB 1074865 A	05-07-1967
			NL 7208255 A	08-03-1973
			NL 7208555 A	25-08-1972
			NL 7208572 A	25-08-1972
			NO 115124 B	29-07-1968
			NO 123227 B	18-10-1971
			SE 324703 B	08-06-1970
			SE 312980 B	28-07-1969
			SE 312981 B	28-07-1969
			US 3352218 A	14-11-1967
			US 3345925 A	10-10-1967
EP 0722183	A	17-07-1996	JP 8250068 A	27-09-1996
			DE 69616605 D1	13-12-2001
			EP 0722183 A2	17-07-1996
			US 5783907 A	21-07-1998
EP 0284576	A	28-09-1988	SE 457760 B	23-01-1989
			CN 88101485 A	05-10-1988
			DD 268329 A5	24-05-1989
			DK 154888 A	24-09-1988
			EP 0284576 A2	28-09-1988
			FI 881339 A	24-09-1988
			HU 46165 A2	28-09-1988
			JP 1063242 A	09-03-1989
			NO 881276 A	26-09-1988

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 30 9263

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

31-01-2002

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0284576 A		SE 8701184 A	24-09-1988
		US 4881007 A	14-11-1989
EP 0220633 A	06-05-1987	BR 8605276 A	28-07-1987
		DE 3680070 D1	08-08-1991
		EP 0220633 A1	06-05-1987
		JP 1982235 C	25-10-1995
		JP 7011944 B	08-02-1995
		JP 62110251 A	21-05-1987
		MX 168440 B	25-05-1993
JP 60020446 A	01-02-1985	NONE	
JP 10247476 A	14-09-1998	NONE	
US 5635794 A	03-06-1997	DE 9207139 U1	16-07-1992
		CA 2096905 A1	27-11-1993
		CN 1081021 A ,B	19-01-1994
		DE 59304649 D1	16-01-1997
		EP 0572835 A1	08-12-1993
		HK 1000610 A1	09-04-1998
		HU 213968 B	28-11-1997
		JP 6036743 A	10-02-1994